

## Black Hawk Metals

Brass, Bronze, Cast Iron & Copper.

Em

Australia Tel: 07 3139 1474 s@blackhawkmetals.com.au

ABN: 29 619 485 568 33 Colebard Street West

Acacia Ridge QLD 4110

Email: sales@blackhawkmetals.com.au Web: www.blackhawkmetals.com.au

## **Data Sheet**

LG2 Bronze – Alloy C83600

All BHM material has been manufactured, tested & inspected, and is in compliance with BS1400-C83600 as specified below

TYPICAL CHEMICAL COMPOSITION %	
Element	Nominal
Copper (Cu)	Balance
Tin (Sn)	4.55
Lead (Pb)	5.70
Zinc (Zn)	5.85
Nickel (Ni)	0.5
Silicon (Si)	0.02
Aluminium (Al)	0.01
Phosphor (P)	0.05

## **Typical Mechanical Properties**

Ultimate Tensile Strength	280 MPa
Elongation	30 %
Typical Hardness	70 BHN
Machinability	84 %
Proof Strength	115 MPa

Black Hawk Metals will not be held responsible for the suitability, reliability or accuracy of the information provided on this document. Black Hawk Metals attempts to keep the information on this document up to date, however this may vary with product on hand.