

Black Hawk Metals

The preferred supplier of Brass, Bronze, Cast Iron & Copper.

Tel: 07 3139 1474 Email: sales@blackhawkmetals.com.au Web: www.blackhawkmetals.com.au

ABN: 29 619 485 568 33 Colebard Street West

Australia

Acacia Ridge QLD 4110

Data Sheet

PHOSPHOR BRONZE - Alloy PB1

This material has been manufactured, tested & inspected, and is in compliance with BS1400-PB1 as specified below

TYPICAL CHEMICAL COMPOSITION %	
Element	Nominal
Copper (Cu)	Balance
Tin (Sn)	10.60
Lead (Pb)	0.25
Zinc (Zn)	0.05
Nickel (Ni)	0.1
Silicon (Si)	0.02
Aluminium (AI)	0.01
Phosphor (P)	0.625

Typical Mechanical Properties

Ultimate Tensile Strength 390 MPa

Elongation 8 %

Typical Hardness 110 BHN

Machinability 20 % (free machining brass = 100%)

Proof Strength 190 MPa

Black Hawk Metals will not be held responsible for the suitability, reliability or accuracy of the information provided on this document. Black Hawk Metals attempts to keep the information on this document up to date, however this may vary with product on hand.